



Shandong Lanjing Energy Saving Technology Co.,LTD

Clear with Reflective glass performance data

Glass Configuration	COLOR OF REFLECTION	VISIBALE LIGHT			SOLOR ENERGY		U-VALUE W/m2.k		SC	SHGC
		VLT	VLRO	VLRI	SET	SERO	UVW	UVS		
6JXBG11-08(T)	Silver Grey	8	43	40	14	33		4.5	0.23	0.2
6JXBG11-14(T)	Silver Grey	14	36	24	16	30		4.7	0.29	0.25
6JXBG11-20(T)	Silver Grey	20	29	25	18	25		4.8	0.35	0.3
6JXBG11-30(T)	Silver Grey	30	22	18	25	24		4.9	0.45	0.39
6JXBG11-40(T)	Silver Grey	40	21	12	30	18		5	0.51	0.44
6JXBG11-50(T)	Blue Grey	50	19	13	45	16		5.1	0.64	0.55
6JXBG11-60(T)	Blue Grey	60	14	17	57	11		5.2	0.75	0.65
6JXBG11-70(T)	Blue Grey	70	19	21	68	16	5.5	5.1	0.83	0.72
6JXNG11-80(T)	Neutral	80	17	20	78	15	5.7		0.84	0.72

1, The above performance data calculated by NFRC300-2003, NFRC100-2010;OPTICS 6, And WIMDOW 6.3

2, The above performance data was only for reference. Testing data of the actual products will have some slight deviation from the calculated

