



Shandong Lanjing Energy Saving Technology Co.,LTD

Single Low E IGU performance data

GOODS DESCRIPTION	COLOR OF REFLECTION	VISIBALE LIGHT			SOLOR ENERGY		U-VALUE W/m2.k		SC VALUE	SHGC
		VLТ	VLRO	VLRI	SET	SERO	UVW	UVS		
6mm Optisolar S40 +12A+6C	Silver Grey	38	35	13	23	33	1.8	1.79	0.34	0.29
6mm Clear with S50 +12A+6C	Light Grey	45	22	11	28	23	1.85	1.85	0.4	0.35
6mm Optisolar S50II+12A+6C	Light Grey	45	27	11	27	29	1.77	1.76	0.38	0.33
6mm Optisolar S49 +12A+6C	Silver Grey	45	34	12	25	35	1.73	1.7	0.36	0.31
6mm Optisolar S60 +12A+6C	Grey	55	18	11	34	21	1.86	1.87	0.47	0.41
6mm Optisolar S70 +12A+6C	Blue Grey	62	17	12	38	20	1.86	1.87	0.52	0.45
6mm Optilite 83 +12A+6C	Neutral	75	12	13	46	20	1.75	1.72	0.61	0.53

1, The above performance data calculated by NFRC300-2003, NFRC100-2010;OPTICS 6, And WIMDOW 6.3

2, The above performance data was only for reference. Testing data of the actual products will have some slight deviation from the calculated